

**PRODUCT DESCRIPTION**

SSP083 is a 60 durometer heat cured silicone elastomer. It is designed to meet the fuel resistant requirements outlined in the AMS-3326 specification. This product uses a varox- or dicumyl- peroxide catalyst system. It can be supplied as ready-to-mold compound or as compression molded sheet stock. SSP083 silicone can be pigmented to a customer's requirement, but the most popular colors produced are red, blue, and black.

<b>DATA</b>	<b>Typical Values</b>
<b>Shore A</b> (55 - 65 range)	60
<b>Tensile Strength</b> (900 psi minimum)	1000 psi
<b>Elongation %</b> (175 % minimum)	350%
<b>Tear B</b> (40 ppi min)	150 ppi
<b>Specific Gravity</b>	1.60 – 1.65
*Other tests performed in accordance with AMS-3326 specification include: 22 hours Compression Set, 70 hours Compression Set, Brittle Point, Torsional Stiffness, Youngs Modulus, Shore Change, Tensile Change, Weight Loss %, Oil Immersion, Volume Change %, and Elongation Change.	
<b>Cure Profile:</b> Compression cure for 10 minutes at 177°C (350°F). Post bake for 3 hours at 200°C (390°F).	

\*Certification charges may apply for small quantity orders.

**CATALYZING**

Raw material available catalyzed and ready for press cure molding. Data above was generated with Varox catalyst system.

**SHELF LIFE**

Uncatalyzed – indefinite, may need freshening after 1-2 years. Catalyzed – 6 months. Cold storage will extend shelf life.

**HANDLING & SAFETY**

MSDS information is available on request.

For more information visit [www.sspinc.com](http://www.sspinc.com). To order call (518) 885-8826/ or Fax (518) 885-4682.

**Specialty Silicone Products, Inc.**

Corporate Technology Park \* 3 McCreia Hill Road \* Ballston Spa, NY 12020

**Specialty Silicone Products, Inc is an ISO 9001:2008 registered company.**

Because we cannot foresee or control varied conditions under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.