

## **SSP-502-60V1**

### **Silicone Shielding Flame Retardant Elastomer**

#### **PRODUCT DESCRIPTION**

The SSP502-60V1 is a 60 durometer nickel coated graphite filled flame retardant silicone elastomer. This product conforms to UL-94 V1. This product is supplied as ready-to-mold compound; fully cured, conductive sheet stock; or, for some formulations, continuous rolls. The data below was generated using ASTM test methods and procedures.

<b>DATA</b>	<b>Typical Values</b>
<b>Shore A</b> (55- 65 range)	60
<b>Tensile psi</b> (150 minimum)	220 psi
<b>Elongation %</b> (100 minimum)	160%
<b>Tear "B" ppi</b> (50 min)	70
<b>Specific Gravity</b> (1.97 – 2.03)	2.0
<b>Volume Resistivity ohm / cm</b> (0.04 max)	.02 ohm /cm
<b>UL-94 Flammability Rating</b>	V1
<b>Color</b>	Black
<b>Thermal Stability Range</b>	-60°C - 220°C

#### **CATALYZING**

Raw material available catalyzed and ready for press cure molding. Data above was generated with Varox catalyst system.

#### **SHELF LIFE**

Uncatalyzed – indefinite, may need freshening after 1-2 years. Catalyzed – 6 months. Cold storage will extend shelf life.

#### **HANDLING & SAFETY**

MSDS information is available on request.

For more information visit [www.sspinc.com](http://www.sspinc.com). To order call **(518) 885-8826/** or Fax **(518) 885-4682**.

#### **Specialty Silicone Products, Inc.**

Corporate Technology Park \* 3 McCrea Hill Road \* Ballston Spa, NY 12020

**Specialty Silicone Products, Inc is an ISO 9001:2008 registered company.**

Because we cannot foresee or control varied conditions, under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.