

SSP2529

Corrosion Resistant Silicone Shielding Elastomer

PRODUCT DESCRIPTION

SSP2529 is a 68 durometer silicone that is filled with nickel plated aluminum particles. This product is supplied as fully cured, conductive sheet stock, continuous extrusion profiles, or ready-to-mold compound.

DATA	Method	Typical Values
Shore A (58- 78 range)	ASTM D2240	68
Tensile psi (150 minimum)	ASTM D412	200 psi
Elongation % (100 min)	ASTM D412	320%
Tear "B" ppi (40 min)	ASTM D624	50
Specific Gravity (1.60 – 2.10)	ASTM D792	2.05
Volume Resistivity ohm / cm (0.150 max)	ASTM D991	0.08 ohm /cm
Thermal Conductivity W/mK	-	1.6
Color	-	Dark Gray
Thermal Stability Range	-	-60°C - 220°C
Shielding Effectiveness 20MHZ-10GHZ	MIL-DTL-83528	➤ 110 dB
Galvanic Corrosion 168 Hour Salt Spray	ASTM B117	0.08%

CATALYZING

Raw material available catalyzed and ready for press cure molding. Data above was generated with Varox catalyst system.

SHELF LIFE

Uncatalyzed – indefinite, may need freshening after 1-2 years. Catalyzed – 6 months. Cold storage will extend shelf life.

HANDLING & SAFETY

SDS information is available on request.

For more information visit www.sspinc.com. To order call **(518) 885-8826/** or Fax **(518) 885-4682**.

Specialty Silicone Products, Inc.

Corporate Technology Park * 3 McCrea Hill Road * Ballston Spa, NY 12020

Specialty Silicone Products, Inc is an ISO 9001:2008 registered company.

Because we cannot foresee or control varied conditions, under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.