

SSP-555-65E Shielding Silicone Elastomers

PRODUCT DESCRIPTION

SSP-555-65E is a silver filled conductive silicone elastomer. It is nominally a 65 durometer product. It is supplied as fully cured, conductive sheet stock or ready-to-mold compound. The data below was generated using ASTM test method and procedures.

DATA	Typical Values
Shore A (58-72 range)	65
Tensile psi (300 minimum)	550 psi
Elongation % (200-500 range)	325%
Compression Set % (45 max.)	33% (70 hours at 100°C)
Specific Gravity (3.05 – 3.95)	3.15
Volume Resistivity ohm / cm (0.002 max.)	.001 ohm /cm
Color	Tan
Thermal Stability Range	-60°C - 220°C

CATALYZING

Raw material available catalyzed and ready for press cure molding. Data above was generated with Varox catalyst system.

SHELF LIFE

Uncatalyzed – indefinite, may need freshening after 1-2 years. Catalyzed – 6 months. Cold storage will extend shelf life.

HANDLING & SAFETY

MSDS information is available on request.

For more information visit www.sspinc.com. To order call (518) 885-8826/ or Fax (518) 885-4682.

Specialty Silicone Products, Inc.

Corporate Technology Park * 3 McCrea Hill Road * Ballston Spa, NY 12020

Specialty Silicone Products, Inc is an ISO 9001:2008 registered company.

Because we cannot foresee or control varied conditions, under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.