



SSP-502F-60
Conductive Fluorosilicone Elastomer

PRODUCT DESCRIPTION

SSP-502F-60 is a Nickel Coated Graphite filled fluorosilicone conductive elastomer. **SSP-502F-60** is a 60 durometer conductive heat cured Fluorosilicone Elastomer. Operating temperatures on the cured elastomer is -55C to 200C. Please store uncured elastomer at 33C in a clean dry container. Storage life of the uncured elastomer at the above temperature is 6 months.

DATA

Shore A

Tensile psi

Elongation %

Tear "B" ppi

Specific Gravity

Volume Resistivity

Compression Set %

Compression/Deflection %

Temperature Range °C

Color

Typical Values

58-68

225

350

45

2.20

0.02

45

3.5

-55 + 200

Dark Gray

STORAGE

6 months from date of shipment of the material, stored in original unopened containers.

SHELF LIFE

Uncatalyzed – indefinite, may need freshening after **1-2** years. Catalyzed – **6-12 months**. Cold storage will extend shelf life.

HANDLING & SAFETY

MSDS information is available on request.

For more information or to place an order, call **(518) 885-8826/Fax (518) 885-4682**

Specialty Silicone Products, Inc is Registered ISO 9001.

Specialty Silicone Products, Inc.

Corporate Technology Park * 3 McCrea Hill Road * Ballston Spa, NY 12020

Because we cannot foresee or control varied conditions, under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.

Data502F-60.doc 04/22/04