

Conductive Fluorosilicone Elastomer

PRODUCT DESCRIPTION

SSP-550-45 is a Silver Plated Aluminum filled fluorosilicone conductive elastomer. This product is supplied as fully cured, conductive sheet stock, continuous extrusion profiles, or ready-to-mold compound. The data below was generated using ASTM test method and procedures. SSP550-45 was designed to meet the requirements outlined in the MIL-G-83528C specifications.

| DATA | Typical Values |
|---|-------------------------|
| Shore A (40-50 range) | 45 |
| Tensile psi (150 minimum) | 185 psi |
| Elongation % (300 minimum) | 350% |
| Compression Set % (30 max.) | 21% (70 hours at 100°C) |
| Specific Gravity (1.75 – 2.25) | 2.08 |
| Volume Resistivity ohm / cm (0.012 max.) | .002 ohm /cm |
| Color | Tan |
| Thermal Stability Range | -60°C - 220°C |
| Thermal Conductivity W/mK | 1.24 |

CATALYZING

Raw material available catalyzed and ready for press cure molding. Data above was generated with Varox catalyst system.

SHELF LIFE

Uncatalyzed – indefinite, may need freshening after 1-2 years. Catalyzed – 6 months. Cold storage will extend shelf life.

HANDLING & SAFETY

MSDS information is available on request.

For more information visit www.sspinc.com. To order call **(518) 885-8826/** or Fax **(518) 885-4682**.

Specialty Silicone Products, Inc.

Corporate Technology Park * 3 McCrea Hill Road * Ballston Spa, NY 12020

Specialty Silicone Products, Inc is an ISO 9001:2008 registered company.

Because we cannot foresee or control varied conditions, under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.